

# Bentonite



| Parameters                             | Specification                                          |                    |
|----------------------------------------|--------------------------------------------------------|--------------------|
| Bentonite types                        | API 13A Section 9                                      | API 13A Section 11 |
| Viscometer dial reading at 600 rpm     | 30 Min                                                 |                    |
| Yield point/Plastic viscosity ratio    | 3 Max                                                  | 6Max               |
| Filtrate volume, cm3                   | 15cm3 MAX                                              | 16 cm3 MAX         |
| Residue of diameter greater than 75 mm | 4% MAX                                                 | 2.5 % MAX          |
| Fineness (Dry mesh passing through)    |                                                        |                    |
| 100 BSS mesh                           | 99% Min                                                | 99% Min            |
| 200 BSS mesh                           | 85 % Min                                               | 85 % Min           |
| Packing                                | 25 KG in 1 Ton Bag / 2 Ton Bulk Bag                    |                    |
| Applications                           | Ceramics Industry / Fertilizer Industry / Pet Products |                    |